

OFFICE OF NAVAL RESEARCH

4

Contract N00014-83-K-0498

R&T Code 413d011---02

Technical Report No. 20

Impedance Studies of the Cell Pt/ Ag<sup>+</sup> Conducting Glass/  
Ag Beta" Alumina/Pt

by

H. Durakpasa, P. Linhardt and M.W. Breiter

Prepared for Publication

in

Electrochimica Acta

AD-A209 820  
DTIC  
ELECTE  
JUN 26 1989  
S D

Technische Universität Wien  
Institut für Technische Elektrochemie  
9, Getreidemarkt, 1060 Wein, Austria

June 15, 1989

Reproduction in whole or in part is permitted for  
any purpose of the United States Government.

This document has been approved for public release and sale;  
its distribution is unlimited.

30

035

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE

## REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS	
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for public use and sale; its distribution is unlimited	
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE				
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report No. 20			5. MONITORING ORGANIZATION REPORT NUMBER(S)	
6a. NAME OF PERFORMING ORGANIZATION Department of Materials Science and Engineering		6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION Office of Naval Research	
6c. ADDRESS (City, State, and ZIP Code) 6531 Boelter Hall University of California, Los Angeles Los Angeles, CA 90024-1595			7b. ADDRESS (City, State, and ZIP Code) Chemistry Division 800 N. Quincy Street Arlington, VA 22217	
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-83-K-0498	
8c. ADDRESS (City, State, and ZIP Code) Chemistry Division 800 N. Quincy Street Arlington, VA 22217			10. SOURCE OF FUNDING NUMBERS	
			PROGRAM ELEMENT NO.	PROJECT NO.
11. TITLE (Include Security Classification) Impedance Studies of the Cell Pt/Ag <sup>+</sup> Conducting Glass/Ag $\beta$ " Alumina/Pt				
12. PERSONAL AUTHOR(S) H. Durakpasa, P. Linhardt, M. W. Breiter				
13a. TYPE OF REPORT Technical		13b. TIME COVERED FROM 8/88 TO 7/89		14. DATE OF REPORT (Year, Month, Day) 1989, June 15
15. PAGE COUNT 9				
16. SUPPLEMENTARY NOTATION Submitted to Electrochimica Acta				
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number) Solid electrolyte, interfacial studies, impedance measurements	
FIELD	GROUP	SUB-GROUP		
19. ABSTRACT (Continue on reverse if necessary and identify by block number)  The qualitative comparison of the impedance behavior of the three cells Pt/ Ag <sup>+</sup> conducting glass/ Ag $\beta$ " alumina; Pt/ glass/ Pt and Pt/ $\beta$ "/ Pt leads to the conclusion that the properties of the cell Pt/ glass/ $\beta$ "/ Pt are determined by those of the interfaces Pt/ glass and $\beta$ "/ Pt at low and intermediate frequencies. At high frequencies the contributions of the bulk impedances become predominant. A contribution from the impedance of the interface glass/ $\beta$ " is small with respect to the other contributions. The transfer of the Ag <sup>+</sup> ion from the amorphous glass phase into the crystalline $\beta$ " alumina is rapid.				
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a. NAME OF RESPONSIBLE INDIVIDUAL Bruce Dunn			22b. TELEPHONE (Include Area Code) (213) 825-1519	22c. OFFICE SYMBOL

IMPEDANCE STUDIES OF THE CELL Pt/ Ag<sup>+</sup> CONDUCTING GLASS/ Ag BETA"  
ALUMINA/ Pt

H.Durakpasa, P.Linhardt and M.W.Breiter

Institut für Technische Elektrochemie, TU Wien, 9 Getreidemarkt,  
A-1060 Wien


ABSTRACT

The qualitative comparison of the impedance behavior of the three cells Pt/ Ag<sup>+</sup> conducting glass / Ag beta" alumina/ Pt, Pt/ glass/ Pt and Pt/ beta"/ Pt leads to the conclusion that the properties of the cell Pt/ glass/ beta"/ Pt are determined by those of the interfaces Pt/ glass and beta"/ Pt at low and intermediate frequencies. At high frequencies the contributions of the bulk impedances become predominant. A contribution from the impedance of the interface glass/ beta" is small with respect to the other contributions. The transfer of the Ag<sup>+</sup> ion from the amorphous glass phase into the crystalline beta" alumina is rapid.

INTRODUCTION

Studies of the kinetics of the transfer of the conducting ion from a solid electrolyte 1 into an electrolyte 2 have been mainly carried out in systems where the electrolyte 2 was liquid. Aqueous electrolytes were used for silver ion conductors, especially AgI (1 - 4) and Ag<sub>3</sub>SI (5,6). Sodium ion conductors were investigated (7,8) in organic electrolytes.

Little work has been reported (9,10) for systems in which both electrolytes were solids. A previous paper (11) involved impedance studies of the symmetrical cell Ag/ AgI/ Ag beta" alumina/ AgI/ Ag. An attempt was made there to obtain information on the silver ion transfer between two crystalline solid electro-



Codes

A-1

lytes. General interest exists in studies of the properties of the interface between two solid electrolytes for batteries (12) and sensors (9,13).

The asymmetric cell Pt/ Ag<sup>+</sup> conducting glass/ Ag beta" alumina/ Pt was chosen here. This cell incorporates an interface between an amorphous and a crystalline solid electrolyte. Pt electrodes were taken because previous work (14) on the interface Ag/ Ag beta" alumina revealed a relatively complicated behavior. Impedance spectroscopy served again as the technique in the present work.

#### EXPERIMENTAL SECTION

The silver ion conducting glass consisted of 34 mole% AgI, 26 mole% Ag<sub>2</sub>O and 40 mole% B<sub>2</sub>O<sub>3</sub>. It was chosen because of its relatively high glass transition temperature of 340°C. Thin slices of this glass were attached to a rectangular piece of Ag beta" alumina, obtained by ion exchange of Ceramtec Na beta" alumina. This was accomplished by heating the glass on top of the polished ceramic to just below its melting temperature and turning the furnace off. The glass surface was polished by hand. Platinum was sputtered onto the glass surface on one side and onto the polished surface of the ceramic on the other side. Contacts between the platinum films and the wire leads of the measuring system were made by silver paint. The cell was inside a glass vessel under N<sub>2</sub>. The glass vessel was inside a furnace heated by DC current. The temperature was controlled by a temperature controller.

The measurements of the cell impedance were made at constant temperature in the frequency range 10<sup>-2</sup> to 10<sup>5</sup> Hz by the IM 5E automated impedance meter of Zahner-elektrik (F.G.R.). It was

found necessary to heat the cell to the highest temperature (320°C) and start the measurements there. Subsequently the temperature was decreased stepwise to room temperature and increased again. Reproducible results could be obtained if the measurements were repeated in this way.

For comparison similar measurements were carried out under the same conditions on the simpler cells Pt/ Ag<sup>+</sup> conducting glass/ Pt (15) and Pt/ Ag beta" alumina/Pt.

## RESULTS

Results of the impedance measurements are shown at three different temperatures for the said cells in Fig.1 to Fig.3. The data are presented in a Bode plot which is directly available by a program delivered with the impedance meter. In general, plots of this type were found satisfactory for the interpretation.

## DISCUSSION

The cell impedance consists of:

$$(1) \quad Z = Z_{\text{Pt/glass}} + Z_{\text{glass/beta}''} + Z_{\text{beta}''/\text{Pt}} + Z_{\text{glass}} + Z_{\text{beta}''}$$

Three interfacial impedances ( $Z_{\text{Pt/glass}}$ ,  $Z_{\text{glass/beta}''}$ ,  $Z_{\text{beta}''/\text{Pt}}$ ) and two bulk impedances ( $Z_{\text{glass}}$ ,  $Z_{\text{beta}''}$ ) are involved. Excepting the lower temperature range, the impedances  $Z_{\text{glass}}$  and  $Z_{\text{beta}''}$  may be considered ohmic in the frequency range under consideration here. It will be shown subsequently that this statement is in agreement with the experimental results.

It was planned originally to determine the interfacial impedances  $Z_{\text{Pt/glass}}$  and  $Z_{\text{beta}''/\text{Pt}}$  separately from the measurements on the cells Pt/ glass/ Pt and Pt/ beta"/ Pt and to subtract the values at a given frequency and temperature from those of  $Z$ .

However, the reproducibility of the impedance data from cell to cell was found to depend strongly upon the preparation of the sputtered electrodes and their heat treatment. Thus the outlined procedure had to be replaced by a qualitative comparison of the impedance plots.

The plots of the logarithm of the absolute value of the cell impedance versus the logarithm of the frequency display a relatively simple behavior at 150° and 300°C in Fig.1 and at all three temperatures in Fig.2. The absolute values decrease and approach a practically constant value at high frequencies. The constant value can be assigned to  $R_{\text{glass}} + R_{\text{beta}}$  in Fig.1 and to  $R_{\text{glass}}$  in Fig.2. The bulk resistances  $R_{\text{glass}}$  and  $R_{\text{beta}}$  were also estimated from separate four-probe measurements of the bulk conductivities of the two solid  $\text{Ag}^+$  ion conductors and the geometric dimensions. The computed values agreed reasonably well with the experimental values at high frequencies at the said temperatures. The fact that  $R_{\text{glass}}$  is considerably smaller than  $R_{\text{beta}}$  is reflected by the lower values of  $Z$  in Fig.2 than in Fig.1 at high frequencies. The absolute value of the impedance does not approach a constant value at high frequencies at 25°C in Fig.1 because the influence of the grain boundary impedance on  $Z_{\text{beta}}$  becomes visible at the low temperature. A different effect is responsible that  $R_{\text{beta}}$  is approached in Fig.3 at high frequencies, but not reached. It is suggested that an additional process the nature of which is not known at present becomes effective at high frequencies. It is not possible to separate the contribution of this process from bulk contributions.

The phase angle and the absolute value of the impedance in Fig.1 and Fig.3 display the properties of a constant phase element at low frequencies in a first approximation. In Fig.2

such a behavior is only seen at 25°C. The latter result can be explained by a system with blocking electrodes. The phase angle approaches values which do not differ much from 90° ( theoretical value of a capacitor ). Somewhat lower average values of the phase angle are observable at low frequencies in Fig.1. While these values in Fig.1 might still be assigned to an interface with blocking electrodes, this is not feasible in Fig.3 any longer. The average values of the phase angle at low frequencies have become too different from 90° to assign them to blocking electrodes. Probably Faradaic processes at the interface beta"/Pt are involved. The reader is referred for a discussion of the results at 150° and 300° in Fig.2 to reference 15.

The qualitative comparison of the low- frequency behavior of the cell impedances shows that the properties of the cell Pt/ glass/ beta"/ Pt lie between those of the cells Pt/ glass/ Pt and Pt/ beta"/ Pt. It appears that the contributions of both interfaces ( Pt/ glass and beta"/ Pt ) to the impedance determine its behavior.

The behavior of the impedance of the cell Pt/ glass/ beta"/ Pt could be interpreted in a qualitative fashion for low and high frequencies. A contribution of the interface glass/ beta" to the total impedance could not be detected. It has to be small with respect to the other contributions. It follows that the transition of the Ag<sup>+</sup> ion from the amorphous electrolyte into the crystalline electrolyte has to be rapid.

#### ACKNOWLEDGEMENT

The preparation of the glass by the group of Prof.B.Dunn at UCLA/USA is gratefully acknowledged. The investigations were made with partial support by the Office of Naval Research.

## REFERENCES

1. J.H.A.Pieper and D..A.de Vooy, J.Electroanalyt.Chem. 53, 243 (1974)
2. D.A. de Vooy and J.H.A.Pieper, *ibid.* 72, 147 (1976)
3. K.J.Peverelli and H.P.Van Leeuwen, *ibid.* 110, 119 and 137 (1980)
4. K.Kvastek and V.Horvat, *ibid.* 130, 67 (1981) and 147, 83 (1983)
5. Yu.V.Shirokov, V.S.Borovkov and P.D.Lukovtsev, *Elektrokhim.* 5, 1211 (1969)
6. Yu.V.Shirokove, P.D.Lukovtsev and V.S.Borovkov, *ibid.* 7, 393 and 575 (1971)
7. M.Voinov and H.Tannenberger, *Electrochim. Acta* 19, 959 (1974)
8. G.C.Farrington, *Electrocatalysis on Non-Metallic Surfaces*, A.D.Franklin, ed., NBS Special Publication 455, 341 (1976)
9. P.Fabry, E.Schouler and H.Kleitz, *Electrochim.Acta* 23,539 (1978)
10. A.M.Mikhailova and E.A.Uksche, *Elektrokhim.* 15, 1242 (1979)
11. M.W.Breiter, H.Drstak and M.Maly-Schreiber, *Solid State Ionics* in print
12. J.F.Kennedy, *Thin Solid Films* 43, 41 (1977)
13. M.Gauthier and D.Fauteux, *J.Electrochem.Soc.* 131, 579 (1984)
14. M.W.Breiter, H.Drstak and M.Maly-Schreiber, *J.Electroanalyt. Chem.* 228, 417 (1987)
15. H.Durakpasa, P.Linhardt and M.W.Breiter, *Solid State Ionics*, submitted to print

## FIGURE CAPTIONS

Fig.1: Bode plot of impedance data for the cell Pt/ Ag<sup>+</sup> conducting glass/ Ag beta" alumina/ Pt at different temperatures.

Fig.2: Bode plot of impedance data for the cell Pt/ Ag<sup>+</sup> conducting glass/ Pt at different temperatures.

Fig.3: Bode plot of impedance data for the cell Pt/ Ag beta" alumina/ Pt at different temperatures.






Fig. 1





Fig.2





Fig. 3